



## 72001 / 72004 Jet Black Basecoat

### DESCRIPTION:

**Jet Black Basecoat** is a direct replacement for PPG DBC 9700 which is used in the DBU basecoat systems. **Jet Black Basecoat** is available in an F-style gallon and a round quart.

### INSTRUCTIONS:

Shake can thoroughly before use. Mix **Jet Black Basecoat** with standard urethane grade reducer at a 1:1 mix ratio (100%). Stir thoroughly and pour through a strainer into the paint cup. Reseal after each use.

#### Fast Urethane Reducer

#### Medium Urethane Reducer

#### Slow Urethane Reducer

#### Ex-Slow Urethane Reducer

**Note:** For increased durability add 10% of the clearcoat activator to the mixed basecoat

### APPLICATION:

Apply 2-3 medium wet coats or until proper hiding is achieved. Allow 5-10 minutes flash time between coats.

### Technical Data Information

#### V.O.C.

Regulatory:	5.41 lbs/gal. (648g/l)
Actual:	5.41 lbs/gal. (648g/l)
Flash Time between coats	5 minutes
Dust Free Time	5 minutes
Tack Free Time	10 minutes
Spray to coverage	2-3 coats
Coverage @ 1 mil	N/A
Time to topcoat with clearcoat	25-30 minutes
Gun Set-up	
Gravity Fed	1.3mm-1.4mm fluid tip
Mini Jet	1.2mm-1.4mm fluid tip
Air Pressure @ Gun	40-45 psi

**DISCLAIMER:** PPG, Deltron and Concept are registered trade names of PPG. PPG does not manufacture, endorse or guarantee Excel products.

**DISCLAIMER:** Matrix is a registered trade mark name of Matrix System Automotive Finishes. Matrix does not manufacture, endorse or guarantee Excel products.