



76001 / 76004 Basecoat White

DESCRIPTION:

Basecoat White is a direct replacement for PPG DMD 1684 White Base and Matrix MT-84 White Basecoat which is also used as the white tint for DBC and DBU basecoat systems. **Basecoat White** is available in quarts and gallons.

FEATURES:

INSTRUCTIONS:

Agitate thoroughly before use. Use according to paint manufacturers' mixing recommendations. Reseal after each use. **Basecoat White** should be placed on a mixing machine.

APPLICATION:

Apply product according to paint manufacturers' recommendations.

V.O.C.

Regulatory:
5.2 lbs/gal. (623 g/l)
Actual
5.2 lbs/gal (623 g/l)

Basecoat White reduces 1:1 (100%) with the Urethane Grade reducers.

80 Fast Urethane Reducer
Medium Urethane Reducer
Slow Urethane Reducer
X-Slow Urethane Reducer

Technical Data Information (Basecoat)

Flash Time between coats	5 minutes
Dust Free Time	5 minutes
Tack Free Time	5 minutes
Spray to coverage	2-3 coats
Dry to sand time (air dry)	10-15 minutes
Time to recoat with basecoat	10-15 minutes
Time to topcoat with clearcoat	25-30 minutes
Gun Set-up	1.3mm-1.4mm fluid tip
Air Pressure @ Gun	40-45 psi

Part Numbers

76001 Basecoat White-gallon (4 per case)
76004 Basecoat White-quart (6 per case)

DISCLAIMER: PPG, Deltron and Concept are registered trade names of PPG. PPG does not manufacture, endorse or guarantee Excel refinish products.



Technical Data Sheet

Page 2 of 2

DISCLAIMER: Matrix is a registered trade mark name of Matrix System Automotive Finishes. Matrix does not manufacture, endorse or guarantee Excel refinish products.